## In the Claims:

Amend the claims 1, 6, 8 and 15 to read as follows:

5%)

1. (Thrice Amended) Support material coated on at least one side with a synthetic resin, containing a raw paper provided at least on the front side with a pigment coating, wherein the synthetic resin is a polyolefin resin on the pigment coating, and wherein the pigment coating contains at least about 5% by weight of a pigment having particles with a narrow grain distribution with respect to the weight of the total pigment in the pigment layer, whereby at least about 70% by weight of the pigment particles have a size of less than about  $1\mu m$  and at least 40% by weight of the particles have a grain size of 0.35 to  $0.8\mu m$ .

67

6. (Once Amended) Support material coated on at least one side with synthetic resin, containing a raw paper provided on at least the front side with a pigment coating, wherein the synthetic resin is a polyolefin resin on the pigment coating, and wherein the pigment coating contains calcium carbonate which has a surface modified by an inorganic substance in platelet shape.

8. (Once Amended) Support material according to claim 6, wherein the proportion of the surface modified calcium carbonate pigment in the total amount of pigment amounts to at least about 5% by weight.

15. (Thrice Amended) Support material for an ink-jet recording sheet comprising a raw paper provided at least on the front side with a pigment coating, wherein the synthetic resin is a polyolefin resin on the pigment coating, and wherein the pigment coating contains at least about 5% by weight of a pigment having particles with a narrow grain distribution with respect to the weight of the total pigment in the pigment layer, whereby at least about 70% by weight of the pigment particles have a size of less than about  $1\mu m$  and at least 40% by weight of the particles have a grain size of 0.35 to  $0.8\mu m$ .

Cancel claims 7, 9 and 19

Add new claims 21-23 as follows:

- 21. Support material according to claim 1, wherein the synthetic resin is present in the amount of 5 to 30g/m<sup>2</sup>.
- 22. The support material according to claim 6, wherein the synthetic resin is present in the amount of 5 to  $30g/m^2$ .
- 23. The support material according to claim 15, wherein the synthetic resin is present in the amount of 5 to  $30g/m^2$ .

## **REMARKS**

Claims 1-20 were originally presented for examination. 1

The Examiner has correctly noted that the original claims were 1-19, however there were two claims numbered "9". The